



# MACHINING CONDITIONS

RDMT 1003 M0 LT30

M0001875

Material Group	Lamina Group	Material Example	Hardness	D.O.C		Feed		Vc		Advised D.O.C [mm]	Advised Feed [mm/t]	Advised Vc [m/min]
				min[mm]	max[mm]	min[mm/t]	max [mm/t]	min [m/min]	max [m/min]			
Steel	Non Alloyed	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.5	2.5	0.18	0.64	190	330	1	0.34	250
			190 HB	0.5	2.5	0.18	0.64	190	300	1	0.34	220
			250 HB	0.5	2.5	0.18	0.64	190	250	1	0.34	200
Steel	Low Alloyed	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	230 HB	0.5	2.5	0.15	0.5	150	210	1	0.3	180
			280 HB	0.5	2.5	0.15	0.44	130	190	1	0.27	150
			180 HB	0.5	2.5	0.15	0.5	150	240	1	0.3	200
			350 HB	0.5	2.5	0.15	0.44	130	170	1	0.27	140
Stainless Steel	High Alloyed	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.5	1.8	0.12	0.44	90	150	0.8	0.27	130
			280 HB	0.5	1.8	0.12	0.44	90	130	0.8	0.27	120
			320 HB	0.5	1.8	0.12	0.36	60	110	0.8	0.24	100
			350 HB	0.5	1.8	0.12	0.36	60	90	0.8	0.24	80
Stainless Steel	Austentic	304, 316, X5CrNi18-9	180 HB	0.5	2.5	0.15	0.5	190	250	1	0.3	220
	Duplex		240 HB	0.5	2.5	0.12	0.44	160	210	1	0.3	190
Cast Iron	Ferritic & Martensitic	410, X6Cr17, 17-4 PH, 430	290 HB	0.5	2	0.12	0.36	70	130	0.8	0.24	100
			310 HB	0.5	2	0.12	0.36	70	120	0.8	0.24	90
			200 HB	0.5	2.5	0.15	0.5	150	210	1	0.3	190
			42 HRc	0.5	2	0.15	0.4	90	150	0.8	0.24	130
Cast Iron	Grey	GG20, GG40, EN-GJL-250, N030B	150 HB	0.5	2.5	0.18	0.64	150	240	1	0.34	200
			200 HB	0.5	2.5	0.18	0.64	150	220	1	0.34	180
			250 HB	0.5	2.5	0.18	0.64	150	190	1	0.34	160
Niti Alloy	Malleable & Nodular	GGG40, GGG70, 50005	150 HB	0.5	2.5	0.15	0.56	100	200	1	0.3	180
			200 HB	0.5	2.5	0.15	0.56	100	180	1	0.3	150
			250 HB	0.5	2.5	0.15	0.56	100	150	1	0.3	130
Niti Alloy	Fe, Ni & Co Based	Incoloy 800	240 HB	0.5	2	0.12	0.36	30	50	0.8	0.24	32
		Inconel 700	250 HB	0.5	2	0.12	0.36	30	50	0.8	0.24	30
		Stellite 21	350 HB	0.5	2	0.12	0.36	30	50	0.8	0.24	30
Niti Alloy	Ti Based	T40	-	0.5	2	0.12	0.36	30	60	0.8	0.24	40
		TiAl6V4	-	0.5	2	0.12	0.4	40	70	0.8	0.27	55
Hardened Materials	Steel Chilled Cast Iron White Cast Iron	G-X300CrMo15	55 HRc	0.3	0.6	0.1	0.28	30	60	0.3	0.18	40
		Ni-Hard 2	400 HB	0.3	0.7	0.1	0.36	40	80	0.4	0.21	50
		X100CrMo13, 440C, G-X260NiCr42	45 HRc	0.3	0.9	0.1	0.36	40	80	0.5	0.21	60
			50 HRc	0.3	0.7	0.1	0.32	40	70	0.4	0.19	55
			55 HRc	0.3	0.6	0.1	0.28	40	60	0.3	0.18	50
Aluminium	Al (>8%Si)	AISI12	130 HB	0.5	2.5	0.18	0.64	200	400	1	0.38	280