



MACHINING CONDITIONS

SEKR 1204 AFTN LT 30

FM000044

Material Group	Lamina Group	Material Example	Hardness	D.O.C		Feed		Vc		Advised D.O.C [mm]	Advised Feed [mm/t]	Advised Vc [m/min]		
				min[mm]	max[mm]	min[mm/t]	max[mm/t]	min[m/min]	max [m/min]					
Steel	Non Alloyed	1	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.5	7	0.18	0.46	190	330	3	0.34	250	
				190 HB	0.5	7	0.18	0.46	190	300	3	0.34	220	
				250 HB	0.5	7	0.18	0.46	190	250	3	0.34	200	
	Low Alloyed	2	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	230 HB	0.5	7	0.15	0.36	150	210	3	0.3	180	
				280 HB	0.5	7	0.15	0.32	130	190	3	0.27	150	
				180 HB	0.5	7	0.15	0.36	150	240	3	0.3	200	
				350 HB	0.5	7	0.15	0.32	130	170	3	0.27	140	
	High Alloyed	3	X40CrMoV5, H18, M42, D3, S6-5-2, 12Ni19	220 HB	0.5	5	0.12	0.32	90	150	2.3	0.27	130	
				280 HB	0.5	5	0.12	0.32	90	130	2.3	0.27	120	
				320 HB	0.5	5	0.12	0.26	60	110	2.3	0.24	100	
				350 HB	0.5	5	0.12	0.26	60	90	2.3	0.24	80	
Stainless Steel	Austentic	4	304, 316, X5CrNi18-9	180 HB	0.5	7	0.15	0.32	190	250	3	0.27	220	
				240 HB	0.5	7	0.12	0.29	160	210	3	0.27	190	
	Duplex	5	X2CrNiN23-4, S31500	290 HB	0.5	5	0.12	0.26	70	130	2.3	0.24	100	
				310 HB	0.5	5	0.12	0.26	70	120	2.3	0.24	90	
	Ferritic & Martensitic	6	410, X6Cr17, 17-4 PH, 430	200 HB	0.5	7	0.15	0.32	150	210	3	0.27	190	
				42 HRc	0.5	5	0.15	0.26	90	150	2.3	0.24	130	
Cast Iron	Grey	7	GG20, GG40, EN-GJL-250, N030B	150 HB	0.5	7	0.18	0.46	150	240	3	0.34	200	
				200 HB	0.5	7	0.18	0.46	150	220	3	0.34	180	
				250 HB	0.5	7	0.18	0.46	150	190	3	0.34	160	
	Malleable & Nodular	8	GGG40, GGG70, 50005	150 HB	0.5	7	0.15	0.41	100	200	3	0.3	180	
				200 HB	0.5	7	0.15	0.41	100	180	3	0.3	150	
NITI Alloy	Fe, Ni & Co Based	9	Incoloy 800, Inconel 700, Stellite 21	250 HB	0.5	7	0.15	0.41	100	150	3	0.3	130	
				350 HB	0.5	5	0.12	0.26	30	50	2.3	0.24	30	
				T40	-	0.5	5	0.12	0.26	30	60	2.3	0.24	40
	Ti Based	10	TiAl6V4	-	0.5	5	0.12	0.29	40	70	2.3	0.27	55	
				G-X300CrMo15	55 HRc	0.5	1.5	0.1	0.2	30	60	0.8	0.18	40
Hardened Materials	Steel Chilled Cast Iron White Cast Iron	11	Ni-Hard 2, X100CrMo13, 440C, G-X260NiCr42	Ni-Hard 2	400 HB	0.5	2	0.1	0.26	40	80	1.1	0.21	50
				45 HRc	0.5	2.5	0.1	0.26	40	80	1.5	0.21	60	
				50 HRc	0.5	1.8	0.1	0.23	40	70	1.1	0.19	55	
				55 HRc	0.5	1.5	0.1	0.2	40	60	0.8	0.18	50	
				AISI12	130 HB	0.5	7	0.18	0.46	200	400	3	0.37	280