



# MACHINING CONDITIONS

## SEKT 12T3 AGSN LT 30

M0000455

Material Group	Lamina Group	Material Example	Hardness	D.O.C		Feed		Vc		Advised D.O.C [mm]	Advised Feed [mm/t]	Advised Vc [m/min]	
				min[mm]	max[mm]	min[mm/t]	max [mm/t]	min [m/min]	max [m/min]				
Steel	Non Alloyed	1	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.5	6	0.18	0.46	190	330	3	0.34	250
				190 HB	0.5	6	0.18	0.46	190	300	3	0.34	220
				250 HB	0.5	6	0.18	0.46	190	250	3	0.34	200
	Low Alloyed	2	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	230 HB	0.5	6	0.15	0.36	150	210	3	0.3	180
				280 HB	0.5	6	0.15	0.32	130	190	3	0.27	150
				180 HB	0.5	6	0.15	0.36	150	240	3	0.3	200
				350 HB	0.5	6	0.15	0.32	130	170	3	0.27	140
	High Alloyed	3	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.5	5	0.12	0.32	90	150	2.3	0.27	130
				280 HB	0.5	5	0.12	0.32	90	130	2.3	0.27	120
				320 HB	0.5	5	0.12	0.26	60	110	2.3	0.24	100
				350 HB	0.5	5	0.12	0.26	60	90	2.3	0.24	80
Stainless Steel	Austentic	4	304, 316, X5CrNi18-9	180 HB	0.5	6	0.15	0.32	190	250	3	0.27	220
	240 HB	0.5		6	0.12	0.29	160	210	3	0.27	190		
	Duplex	5	X2CrNiN23-4, S31500	290 HB	0.5	5	0.12	0.26	70	130	2.3	0.24	100
	310 HB	0.5		5	0.12	0.26	70	120	2.3	0.24	90		
Cast Iron	Ferritic & Martensitic	6	410, X6Cr17, 17-4 PH, 430	200 HB	0.5	6	0.15	0.32	150	210	3	0.27	190
	42 HRc	0.5		5	0.15	0.26	90	150	2.3	0.24	130		
	Grey	7	GG20, GG40, EN-GJL-250, N030B	150 HB	0.5	6	0.18	0.46	150	240	3	0.34	200
	200 HB	0.5		6	0.18	0.46	150	220	3	0.34	180		
	250 HB	0.5		6	0.18	0.46	150	190	3	0.34	160		
Niti Alloy	Malleable & Nodular	8	GGG40, GGG70, 50005	150 HB	0.5	6	0.15	0.41	100	200	3	0.3	180
	200 HB	0.5		6	0.15	0.41	100	180	3	0.3	150		
	250 HB	0.5		6	0.15	0.41	100	150	3	0.3	130		
	Fe, Ni & Co Based	9	Incoloy 800, Inconel 700, Stellite 21	240 HB	0.5	5	0.12	0.26	30	50	2.3	0.24	32
	250 HB	0.5		5	0.12	0.26	30	50	2.3	0.24	30		
	350 HB	0.5		5	0.12	0.26	30	50	2.3	0.24	30		
Hardened Materials	Ti Based	10	T40	-	0.5	5	0.12	0.26	30	60	2.3	0.24	40
			TiAl6V4	-	0.5	5	0.12	0.29	40	70	2.3	0.27	55
	Steel Chilled Cast Iron White Cast Iron	11	G-X300CrMo15	55 HRc	0.5	1.5	0.1	0.2	30	60	0.8	0.18	40
			Ni-Hard 2	400 HB	0.5	2	0.1	0.26	40	80	1.1	0.21	50
			X100CrMo13, 440C, G-X260NiCr42	45 HRc	0.5	2.5	0.1	0.26	40	80	1.5	0.21	60
				50 HRc	0.5	1.8	0.1	0.23	40	70	1.1	0.19	55
				55 HRc	0.5	1.5	0.1	0.2	40	60	0.8	0.18	50
Aluminium	Al (>8%Si)	12	AISI12	130 HB	0.5	6	0.18	0.46	200	400	3	0.37	280