



MACHINING CONDITIONS

WNMG 080412 NN LT
1000

T0001953

Material Group	Lamina Group	Material Example	Hardness	D.O.C		Feed		Amax [mm^2]	Vc		Advised D.O.C [mm]	Advised Feed [mm/t]	Advised Vc [m/min]		
				min[mm]	max[mm]	min[mm/t]	max [mm/t]		min [m/min]	max [m/min]					
Steel	Non Alloyed	1	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.7	3.5	0.25	0.65	2.16	180	330	2.6	0.48	240	
				190 HB	0.7	3.5	0.25	0.65	2.16	180	280	2.6	0.44	220	
				250 HB	0.7	3.5	0.25	0.59	1.8	180	250	2.6	0.41	200	
	Low Alloyed	2	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	230 HB	0.7	2.8	0.25	0.59	1.44	120	250	2.6	0.4	180	
				280 HB	0.7	2.8	0.22	0.52	1.44	120	210	2.6	0.38	150	
				180 HB	0.7	3.5	0.25	0.59	1.44	120	280	2.6	0.4	200	
				350 HB	0.7	2.5	0.22	0.52	1.2	120	180	2.3	0.38	130	
Stainless Steel	Austentic	3	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.7	2.8	0.22	0.52	1.44	70	190	2.1	0.38	140	
				280 HB	0.7	2.8	0.22	0.52	1.44	70	150	2.1	0.38	120	
	Duplex	5		320 HB	0.7	2.1	0.22	0.46	0.96	70	130	1.9	0.35	100	
				350 HB	0.7	2.1	0.22	0.46	0.96	70	110	1.9	0.35	90	
	Ferritic & Martensitic	6	410, X6Cr17, 17-4 PH, 430	180 HB	0.7	3.5	0.24	0.52	1.44	170	270	2.6	0.31	190	
				240 HB	0.7	3.5	0.24	0.52	1.2	160	220	2.6	0.28	170	
	Grey	7	GG20, GG40, EN-GJL-250, N030B	290 HB	0.7	2.8	0.22	0.46	0.96	80	150	2.1	0.3	100	
				310 HB	0.7	2.8	0.22	0.46	0.96	70	140	2.1	0.3	90	
				200 HB	0.7	3.5	0.22	0.52	0.84	170	250	2.1	0.25	190	
Cast Iron	Malleable & Nodular	8	GGG40, GGG70, 50005	42 HRc	0.7	2.8	0.22	0.52	0.84	120	190	1.9	0.25	130	
				150 HB	0.7	3.5	0.18	0.78	2.4	170	250	2.6	0.44	200	
Niti Alloys	Fe, Ni & Co Based	9		200 HB	0.7	3.5	0.18	0.78	2.16	160	230	2.6	0.44	180	
				250 HB	0.7	3.5	0.18	0.72	2.16	150	210	2.6	0.44	160	
				150 HB	0.7	3.5	0.18	0.65	1.8	120	250	2.6	0.38	180	
Hardenable Materials	Ti Based	10	T40	-	0.7	2.1	0.24	0.46	0.84	40	60	1.7	0.38	45	
				TiAl6V4	-	0.7	2.5	0.24	0.52	0.96	50	70	1.7	0.41	55
Aluminum	Steel Chilled Cast Iron White Cast Iron	11	G-X300CrMo15	55 HRc	0.7	1.1	0.13	0.26	0.36	30	50	0.9	0.19	40	
				Ni-Hard 2	400 HB	0.7	1.4	0.13	0.33	0.48	40	60	1.3	0.23	50
			X100CrMo13, 440C, G-X260NiCr42	45 HRC	0.7	1.8	0.13	0.39	0.72	50	100	1.7	0.31	80	
				50 HRC	0.7	1.4	0.13	0.33	0.48	40	90	1.3	0.25	70	
				55 HRC	0.7	1.1	0.13	0.26	0.36	40	80	0.9	0.23	60	
	Al (≥8%Si)	12	AISI12	130 HB	0.7	4.2	0.24	0.78	2.16	200	400	2.6	0.5	280	

